

**Product: PERFORM-O-SIL 668**    **Hydrophobic Precipitated Silica**

**Description:**    **PERFORM-O-SIL 668**  
 A Silicone Treated Silica with Highest levels of hydrophobicity.

<b>Properties:</b>	<b>Physical Data</b>	<b>Unit</b>	<b>Typical Values</b>
	Specific surface area (BET)	m <sup>2</sup> /g	80
	Average particle size	µm	3-4
	Bulk Density	lbs/ft <sup>3</sup>	8-9
	pH	-	10.5 max
	Form	-	Powder
	Hydrophobicity Level	-	Highest

**Applications:**

<p><b>Application</b></p> <ul style="list-style-type: none"> <li>• Defoamers/Anti-foams</li> <li>• Rheology</li> <li>• Powders</li> </ul>	<p><b>General Functional Properties</b></p> <p>Rheology control, Pigment dispersion,                  Pigment stabilization, Free-flow &amp; Anti-caking                  agent for powders.</p>
-------------------------------------------------------------------------------------------------------------------------------------------	----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

**F.D.A. Status:**    Approved for use under: 21 CFR 176.200, 176.210 & 173.340

**Packaging:**    25 lb. Bags and 450 lb. Super sacks

**Contact:**

<p><b>Performance Process Inc.</b>                  1515 Reidel Drive                  Mundelein, IL. 60060                  Phone: 847-949-4080                  Fax: 847-949-9486</p>	<p><b>Nottingham Company</b> <i>(Div. of Performance Process, Inc)</i>                  1303 Boyd Ave. N.W.                  Atlanta, Ga. 30325                  Phone: 404-351-3501                  Fax: 404-351-7731</p>
---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

The information and statements herein are believed to be reliable, but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. **NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE.** Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.